

**TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371**

294-108 PCT/US

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR

09/936344

INTERNATIONAL APPLICATION NO.
PCT/NL00/00174

INTERNATIONAL FILING DATE
16 March 2000

PRIORITY DATE CLAIMED
17 March 1999

TITLE OF INVENTION

Foodstuff Containing Discrete Starch Particles

APPLICANT(S) FOR DO/EO/US

Pieter Lykle BUWALDA, Ido Pieter BLEEKER, Jakob Roelf WOLTJES, and Cindy SEMEIJN

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☐ This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (24) indicated below.
4. ☒ The US has been elected by the expiration of 19 months from the priority date (Article 31).
5. ☒ A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
 - a. ☐ is attached hereto (required only if not communicated by the International Bureau).
 - b. ☒ has been communicated by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☐ An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)).
 - a. ☐ is attached hereto.
 - b. ☐ has been previously submitted under 35 U.S.C. 154(d)(4).
7. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))
 - a. ☐ are attached hereto (required only if not communicated by the International Bureau).
 - b. ☐ have been communicated by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☒ have not been made and will not be made.
8. ☐ An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. ☐ An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)).
10. ☐ An English language translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).
11. ☒ A copy of the International Preliminary Examination Report (PCT/IPEA/409).
12. ☒ A copy of the International Search Report (PCT/ISA/210).

Items 13 to 20 below concern document(s) or information included:

13. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
14. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
15. ☐ A **FIRST** preliminary amendment.
16. ☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
17. ☐ A substitute specification.
18. ☐ A change of power of attorney and/or address letter.
19. ☐ A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821 - 1.825.
20. ☒ A second copy of the published international application under 35 U.S.C. 154(d)(4).
21. ☐ A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4).
22. ☒ Certificate of Mailing by Express Mail
23. ☐ Other items or information:

EXPRESS MAIL CERTIFICATE

Date 09/10/01 Label No. EL608284826 US

I hereby certify that on the date indicated above, I deposited this paper or fee with the U.S. Postal Service & that it was addressed for delivery to the Assistant Commissioner for Patents, Washington, D.C. 20231 by "EXPRESS MAIL Post Office to Addressee" Service.

CASSANDRA LEMS *Cassandra Lems*

09/936344

PCT/NL00/00174

294-108 PCT/US

24. The following fees are submitted.:

BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)) :

- ☐ Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO \$1000.00
- ☒ International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO \$860.00
- ☐ International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$710.00
- ☐ International preliminary examination fee (37 CFR 1.482) paid to USPTO but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$690.00
- ☐ International preliminary examination fee (37 CFR 1.482) paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4) \$100.00

ENTER APPROPRIATE BASIC FEE AMOUNT =**CALCULATIONS PTO USE ONLY**

\$860.00

Surcharge of \$130.00 for furnishing the oath or declaration later than ☐ 20 ☐ 30 months from the earliest claimed priority date (37 CFR 1.492 (e)).

\$0.00

CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE
Total claims	13 - 20 =	0	x \$18.00
Independent claims	3 - 3 =	0	x \$80.00

\$0.00

\$0.00

Multiple Dependent Claims (check if applicable). ☒

\$270.00

TOTAL OF ABOVE CALCULATIONS =

\$1,130.00

Applicant claims small entity status. (See 37 CFR 1.27). The fees indicated above are reduced by 1/2.

\$0.00

SUBTOTAL =

\$1,130.00

Processing fee of \$130.00 for furnishing the English translation later than ☐ 20 ☐ 30 months from the earliest claimed priority date (37 CFR 1.492 (f)).

\$0.00

TOTAL NATIONAL FEE =

\$1,130.00

Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) (check if applicable). ☐

\$0.00

TOTAL FEES ENCLOSED =

\$1,130.00

Amount to be:

refunded

\$

charged

\$

- a. ☒ A check in the amount of \$1,130.00 to cover the above fees is enclosed.
- b. ☐ Please charge my Deposit Account No. _____ in the amount of _____ to cover the above fees. A duplicate copy of this sheet is enclosed.
- c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 08-2461. A duplicate copy of this sheet is enclosed.
- d. ☐ Fees are to be charged to a credit card. **WARNING:** Information on this form may become public. **Credit card information should not be included on this form.** Provide credit card information and authorization on PTO-2038.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:

Ronald J. Baron, Esq.
Hoffmann & Baron, LLP
6900 Jericho Turnpike
Syosset, New York 11791

Telephone: 516-822-3550
Facsimile: 516-822-3582

SIGNATURE

Ronald J. Baron

NAME

29,281

REGISTRATION NUMBER

10 September 2001

DATE

Rec'd PCT/PTO 10 SEP 2001

Title: FOODSTUFF CONTAINING DISCRETE STARCH PARTICLES

The invention relates to starch used in the food industry, more specifically to starch used in processed foodstuff that, at least in one processing step, is subject to heat and or shear treatment.

5 In nature starch is available in an abundance surpassed only by cellulose as a naturally occurring organic compound. It is found in all forms of green leafed plants, located in their roots, stems, seeds or fruits. Starch serves the plant as food for energy during
10 dormancy and germination. It serves similar purposes for man and animal as well as lower forms of life. Man, however, has found uses for starch that extend far beyond its original design as a source of biological energy. Practically every industry in existence uses starch or
15 its derivatives in one form or another.

In foods and pharmaceuticals starch is used to influence or control such characteristics as texture, aesthetics, moisture, consistency and shelf stability. It can be used to bind or to disintegrate; to expand or to
20 densify; to clarify or to opacify; to attract moisture or to inhibit moisture; to produce short texture or long (stringy) texture, smooth texture or pulpy texture, to produce a (semi)solid gel or a (viscous) fluid, soft coatings or crisp coatings. It can be used to emulsify or
25 to form oil resistant films. Starch can be used to aid processing, packaging, lubrication or moisture equilibration. Starch truly serves as a multifunctional ingredient in the food industry.

The most common sources of food starch are maize,
30 potato, wheat tapioca, and rice. Maize is cultivated in warmer climates, with half of the world's production grown in the USA, its biggest crop. China, the second

largest producer in the world, grows about 10%.
Approximately 70% of the world's potato supply is grown
in the cool, moist, climate of Europe and Russia. Wheat,
requiring a more temperate climate, is primarily grown in
5 the USSR, North America, and Europe. Approximately 90% of
world rice production comes from South and South East
Asia, while tapioca is cultivated in the narrow tropical
band at about the equator.

The building blocks of carbohydrates such as
10 starch are α and β -D glucose which contain six carbon
atoms and form pyranose rings. Through enzymatic
condensation, one molecule of water is split out between
two molecules of glucose to form a bond. This
condensation occurs predominantly between carbons 1 and 4
15 but occasionally between 1 and 6.

Where the α 1,4 linkage develops, a linear chained
homopolymer results which we refer to as amylose. The
length of this chain will vary with plant source but in
general the average length will run between 500 and 2,000
20 glucose units. Traditionally, amylose is considered as
being only linear in configuration but recent
investigations indicate the presence of limited branching
in some amylose molecules.

The second type of polymer in starch develops when
25 the enzymatic condensation between glucose units occurs
at carbons 1 and 6. This occasional linkage, along with
the predominant 1,4 bonding, results in a branching
effect and the development of a molecule much more
massive in size than amylose but with linear chain
30 lengths of only 25-30 glucose units. This molecule is
called amylopectin.

All starches are made up of one or both of these
molecules but the ratio of one to the other will vary
with the starch source. Maize has about 25-28% amylose
35 with the remainder being amylopectin. High amylose maize
can run as high as 80%. Waxy maize has none and tapioca

has about 17% amylose. Potato has about 17-25% amylose with the remainder being amylopectin.

As the plant produces the starch molecules, it deposits them in successive layers around a central hilum to form a tightly packed granule. Wherever possible, adjacent amylose molecules and outer branches of amylopectin associate through hydrogen bonding in a parallel-wise fashion to give radially orientated, crystalline bundles known as "micelles". These micelles hold the granule together to permit swelling in (heated) water without the complete disruption and solubilisation of the individual starch molecules.

These highly orientated and crystalline micellular areas explain the ability of ungelatinised starch granules to rotate the plane of polarised light to produce characteristic interference crosses. This bi-refrangent cross is one of the features used in identifying starch source. When the radial orientation of the crystalline micelle is disturbed, the bi-refrangent cross disappears.

Gelatinisation temperatures are considered as ranges covering the temperatures at which loss of bi-refrangement is first noticed and less than 10% remains. This temperature range is greatly influenced by the binding forces within the granule which vary with species. High amylose maize has much greater bonding force than the other maize varieties due to the high degree of linearity within the granule. On the other hand, ortho phosphate ester groups within the potato granule tend to weaken bonding and lower energy requirements to gelatinise.

When the starch granule is heated in water, the weaker hydrogen bonds in the amorphous areas are ruptured and the granule swells with progressive hydration. The more tightly bound micelles remain intact, holding the granule together. Bi-refrangement is lost. As the granule

continues to expand, more water is imbibed, clarity is improved, more space is occupied, movement is restricted and viscosity increased.

With the swelling of amylose-containing granules, some of the smaller amylose molecules are solubilised and leach out to re-associate into tight bundles which will precipitate if the starch concentration is low or will form a gel if the concentration is high. This is referred to as "set back" or retrogradation. The congealed paste will become cloudy and opaque with time and will eventually release water to shrink into a rubbery consistency.

Waxy maize has essentially no linear amylose molecules so its paste will remain flowable and clear. It will not gel or weep. Tapioca, having a small amount of amylose, gives a soft gel when pasted. Pastes from high amylose starch set to a very stiff gel.

To summarise the physical changes during gelatinisation: the granule swells and loses birefringence; clarity and viscosity increase; and smaller linear molecules dissolve and re-associate to form a gel.

In the unmodified form, starches have limited use in the food industry. Waxy maize starch is a good example. The unmodified granules hydrate with ease, swell rapidly, rupture, lose viscosity and produce weak bodied, very stringy and very cohesive pastes. In general, we modify starch to enhance or repress its inherent properties as appropriate for a specific application. To provide thickening, improve binding, increase stability, to improve mouthfeel and sheen, to gel, disperse or cloud.

In general, we cross-link to control texture and to provide heat, acid and shear tolerance. As a result, we have better control and improved flexibility in dealing with formulation, processing and product shelf-life. Cross-linking of starch in general is thought of as

a means to "spot weld" the granule at random locations, reinforcing hydrogen bonding and inhibiting granule swell and disruption.

This cross-linking treatment strengthens the
5 relatively tender waxy starches so that their cooked
pastes are more viscous and heavy bodied and are less
likely to break-down with extended cooking times,
increased acid or severe agitation. In general cross-link
level of a starch (and in particular of a waxy starch,
10 see for example EP 0 796 868) is selected so that the
product contains many fully swollen, intact granules
after processing and packaging to achieve optimal
viscosity and textural stability.

Another important starch modification is that of
15 stabilisation. This modification prevents gelling and
weeping and maintains textural appearance.

In selecting the proper starch to do the job one
must consider the processing temperature, the length of
time at that temperature and the forces of shear that the
20 pasted starch will encounter. Food starches are for
example used by the dairy industry in a wide variety of
products to provide many desired properties including
viscosity, texture, mouthfeel and improved stability.
Starch selection is particularly important when
25 considering dairy products due to the sensitive nature of
the proteins present in milk. Many factors have to be
considered before a choice of starch can be made;
processing conditions, ingredients and storage
requirements all influence the overall performance of a
30 starch.

The higher the temperature, the greater the shear
and the longer the time exposed to these forces, the more
swollen the granule and the more fragile and susceptible
it is to rupture. We can build in tolerances to shear,
35 temperature and acid by supplementing hydrogen bonds in
the granule by cross-linking.

In general it is desired to reach gelatinisation temperature during processing to ensure that the texture benefits of the starch are fully realised. Two exceptions to this are use of pregelatinised starch and use of
5 starches in cook-up mixes, where the consumer will adequately cook the mix at home. Cooking time, temperature and amount of shear are all important parameters to consider when selecting a starch. Higher temperatures, higher shear rates and longer holding times
10 all increase the degree of cook on a starch. For example, a modified starch can be cooked at 90°C for 10 minutes (to reach optimal viscosity) but needs only 5-15 seconds at Ultra-High-Temperature (UHT) processing at 140°C.

Resistance to shear is considered particularly
15 important in dairy and other products which are subjected to homogenisation. If the product contains a 'cook-up' type starch and is homogenised before cooking, then the starch passes through relatively undamaged. However, if the starch is gelatinised, it must be highly resistant to
20 withstand the high shear encountered to avoid excessive granule rupturing resulting in starch comprising amorphous amylose and/or amylopectine conglomerations rendering the food with a slimy texture.

When foods are heat treated to pasteurisation
25 temperature (75°C), unless the proper starch is selected, the starch paste in the food system may be under-cooked, resulting in a cloudy, thin product. If foods are held at elevated temperatures for extended times, as may be the case in a kettle cook prior to filling, the starch may be
30 over-cooked. This again may result in a product with ruptured starch granules with an undesirably amorphous, long and cohesive texture which makes the mouthfeel of the product slimy, which is in general not wanted by a customer who often prefers a short texture instead.

35 The impact of processing equipment on the starch granule is thus in general considered crucial. Shearing

forces exerted by high speed mixing, milling, homogenisation or pumping can damage the starch granule and make the resulting foodstuff slimy. As mentioned earlier, by cross-linking the starch one in general
5 builds in tolerance to shear as well as to temperature and acid. This is for example a requirement for salad dressing starches which are cooked at low pH, at high temperatures and are also subjected to colloid milling. Pudding starches subjected to flash cooling would be
10 another example of a need for shear tolerance.

However, use of cross-linked starches in foodstuff subject to medium or high shear or temperature treatment has disadvantages as well, as it is in general not possible to provide a starch comprising foodstuff, such
15 as a dessert, a sauce or soup, with a short, smooth or creamy texture and a shiny appearance. In general, use of cross-linked starches in foodstuff subject to shear and heat results in foodstuff having a blind or coarse texture or dull appearance. Empirically, however, it has
20 been found that use of some types of cross-linked waxy cereal starches can result in foodstuff that, albeit somewhat thin because of lack of viscosity depending on the cross-link level used, is at least provided with a reasonably fair shortness, smoothness or shininess.
25 However, often other, more expensive thickeners, such as gums or gelatine, need be used to improve the textural and visual properties of the product and provide resistance to processing conditions such as shear or temperature treatment.

30

The invention provides use of modified starches and methods to use these in foodstuffs (soups, (dairy) desserts, sauces, creams, dressings, fillings and such), that, when used in preparing foodstuff that is subject to
35 heat and/or shear treatment, provide said foodstuff with the so desired smooth, short textures and shiny

appearance, even after prolonged treatment where use of other starches would render the product slimy, coarse or dull.

The invention provides a method for preparing a foodstuff having a short or smooth texture and/or shiny appearance after medium to high heat and/or medium to high shear treatment comprising adding to the ingredients of said foodstuff a cross-linked starch or starch granule selected for its capacity to disintegrate into discrete particles after processing, in particular after heat and/or shear treatment. The invention described herein provides the insight that the textural sensations shortness and smoothness, and the visual sensation shininess, of food comprising starch, are among others related to size and cohesiveness of the starch fragments present in said food. Herein it is found that the presence of discrete starch particles smaller than general swollen starch granule size is beneficial to obtaining a food with those desired characteristics.

In short and oversimplified the insight provided by the invention is that use of a starch that, at least in the end product, after processing, has a large swollen starch granule leaves the food dull and blind, use of a starch having a ruptured granule after processing leaves the food with the slimy amorphous amylose or amylopectin conglomerates, but use of a starch which granules, after processing, disintegrate into cohesive or discrete starch particles smaller than general swollen starch granule size leaves the food short, smooth and/or shiny.

To generate a fat-like mouthfeel, WO89/12403 uses a cross-linked quinoa starch which particles are already very fine (diameter 1 to 5 microns), explicitly avoiding having to use more commonly available starches with much larger granules which are deemed not suitable. The present invention, however, preferably provides use of the more commercially attractive large granule type

starches that are disintegrated from a dispersion into discrete fragments during or before preparing the food product, and does also not resort to making anew fragments from carbohydrate solutions, to provide the
5 desired organoleptic characteristics. Similarly, very fine granule type starches (0. to 4 micron), such as selected from Colacasia esculenta, Saponaria vaccaria, Amaranthus retroflexus, Maranta arundinacea, Wheat B and buckwheat and again not commonly available are used in US
10 5370894, whereas the present invention uses starches with much larger particles to begin with, having average diameters of more than 10, preferably more than 15, and even more preferably more than 20 micron, that are capable to disintegrate from a dispersion into discrete
15 fragments, said fragments providing the desired organoleptic characteristics.

WO98/31240, preferably starting from rice starch which has granule diameters of in general between 2 and 10 micron, mixes raw (non-cross-linked) starches with
20 protein solutions to obtain a texturing agent having distinct size patterns, being mixtures of smaller (e.g. 0.1 to 20 microns) and larger (e.g. 100 to 400) particles.

In a preferred embodiment, the invention provides a
25 method for preparing a foodstuff having a short or smooth texture and/or shiny appearance after medium to high heat and/or medium to high shear treatment comprising adding to said foodstuff a starch comprising cross-linked starch granules capable of disintegrating into discrete
30 particles after heat and/or shear treatment further comprising subjecting said foodstuff to heat and/or shear treatment. As for example can be seen when comparing tables 3 and 4, heat and shear treatment even brings out the desired characteristics when using starch according
35 to the invention.

The invention furthermore provides a method according to the invention wherein said cross-linked starch granules are non-cereal starch granules. For foodstuff, it is in general desirable that a starch be
5 bland or neutral in flavour when used in desserts, sauces, soup-mixes, pie fillings, dressings and the like. The starches generally having the most neutral taste are non-cereal, such as tuber- or root-type, starches, such as potato or tapioca, when compared to starches such as
10 corn, wheat, rice, sorghum, waxy maize and waxy sorghum, which, when incorporated into food, give some undesirable flavour (peculiar to the starch) to the food. These off-flavours have been described by some individuals as 'woody', 'corny', 'starchey', 'bitey' or 'chalkey', and
15 these flavours often come out most poignant after heat treatment. It is now very well possible to avoid these off-flavours in foodstuff subject to heat and/or shear treatment by using a non-cereal starch according to the invention in the preparation of these foods.

20 In a preferred embodiment of a method according to the invention said starch is potato starch, preferably a degraded potato starch, preferably derived from a normal potato, preferably having normal amylose content. Degradation can be achieved by treatment with oxidising
25 agents, or enzymes, or preferably, by treatment with acid, such as by treatment with a mineral acid, such as sulphuric acid or by treatment with sodium hypochlorite. Degrees of degradation are preferably chosen so that a certain measure of disintegration, of course depending on
30 the preferences of the public for which the foodstuff is mainly intended, can be reached after processing, to arrive at the so desired discrete particles providing the desired texture or organoleptic properties, to retain or obtain an essentially short, smooth texture, preferably
35 with shine.

Acid treatment is for example already practised to improve taste (US 4,368,212), but therein not to improve organoleptic characteristics such as texture, mouthfeel and shine.

- 5 Also preferred is a method according to the invention wherein said starch granules are derived from a starch of the so-called waxy type, herein defined as having a amylopectin:amylose ratio of at least 90:10, preferably at least 95:5, more preferably at least 99:1.
- 10 With higher amylopectin content of the granule it is easier to obtain discrete starch particles, especially using low cross-link levels, without degradation. Even more preferred is a starch derived from a waxy-type potato, wherein it is possible to vary most with cross-
- 15 link ratios, especially when compared with waxy corn. Degrees of cross-linking are preferably chosen so that a certain measure of disintegration can be reached after processing, to arrive at the so desired discrete particles providing the desired texture or organoleptic
- 20 properties, to retain or obtain a short, smooth texture, preferably with shine.

- The invention also provides a cross-linked starch granule capable of disintegrating into discrete particles after medium to high heat and/or medium to high shear
- 25 treatment. Said discrete particles are demonstrated in several of the microscopic images given herein, and foodstuff containing such discrete particles can easily be distinguished from other foodstuff by measuring particle size distribution, as exemplified in figure 19.
- 30 In a preferred embodiment, the invention provides a non-cereal starch granule capable of disintegrating into discrete particles after medium to high heat and/or medium to high shear treatment, preferably derived from an acid degraded potato starch or from a potato starch
- 35 having a amylopectin:amylose ratio of at least 90:10, preferably at least 95:5, more preferably at least 99:1,

for example derived from a genetically modified potato plant mutant or from an amylose-free potato plant mutant.

In a preferred embodiment, the invention provides a starch granule according to the invention, 5 said granule having been subjected to cross-linking. Cross-linking starch in itself is a method known in the art and various agents are known. Examples are: epichlorohydrin, sodium trimetaphosphate, phosphorous oxychloride (POCl_3), adipic anhydride, or other reagents 10 with two or more halogen, halohydrin or epoxide groups or combinations which all can be used as cross-linking agents. Preferred are distarch phosphates and distarch adipates. A cross-linked or cross-bonded starch may for example be cross-bonded with 0.003 to 0.024% of adipic 15 anhydride, preferably with 0.01 to 0.03%. Prior to cross-bonding with adipic anhydride the starch may be treated with hydrogen peroxide and/or peracetic acid. Preferably with a quantity which corresponds with 0.001% to 0.045% of active oxygen, most preferably with 0.005 to 0.045%. A 20 distarch phosphate may for example be cross-bonded with sodium trimetaphosphate up to such a degree that the residual phosphate is no more than 0.14% for a potato starch or 0.04% for other starches. Preferably the starch is cross-bonded with 0.01% to 0.25%, most preferably with 25 0.025 to 0.15% of sodium trimetaphosphate, under conditions known to the artisan. Degrees of cross-linking are preferably chosen so that a certain measure of disintegration can be reached after processing. For example, for sodium trimetaphosphate (STMP) cross- 30 linking, 0-5000, preferably 250-2500 mg STMP/kg starch is used, for POCl_3 , 0-400, or 0-200, preferably 40-150 or 75-100 μL POCl_3 / kg starch is used. Of course it is always possible for the artisan to find conditions, possibly in which the reactants react with a low yield, outside of 35 the preferred conditions resulting in a starch with desired properties. A distarch phosphate may as well be cross-bonded with phosphorous oxychloride up to such a degree that the residual phosphate is not more than 0.14%

for a potato starch or 0.4% for other starches. Preferably the starch is cross-bonded with 0.00010 % to 0.01% of phosphorous oxychloride, under conditions known to the artisan. Of course it is always possible for the
5 artisan to find conditions in which the reactants react with a very low yield, outside of the preferred conditions resulting in a starch with the desired properties.

Also preferred is a starch granule according to the
10 invention having been subjected to stabilisation. Stabilisation in general is done by a method known in the art, such as by treatment with acetic anhydride or vinyl acetate, by hydroxyalkylation or comparable treatment. Stabilisation by hydroxyalkylation of starch is for
15 example obtained with reagents containing a halohydrin, or an epoxide group as reactive site. The addition of hydroxypropyl groups is generally performed in aqueous suspensions of starch using propylene oxide, under alkaline conditions. Cross-bonding and/or stabilising
20 reagents are reacted with starch under alkaline conditions. Suitable alkali materials are: sodium hydroxide, potassium hydroxide, ammonium hydroxide, magnesium hydroxide, sodium carbonate and trisodium phosphate. Preferred are the alkali metal hydroxides and
25 carbonates, most preferred are sodium hydroxide and sodium carbonate. Sometimes salts are added as to prevent swelling under alkaline reaction conditions. Preferred are sodium chloride and sodium sulphate. Stabilisation by acetylation is performed using acetic anhydride or vinyl
30 acetate. Other stabilisation reagents are for example succinic anhydride, 1-octenyl succinic anhydride, sodium tripolyphosphate, potassium orthophosphate, sodium orthophosphate or orthophosphoric acid.

The invention also provides foodstuff having been
35 subjected to heat and/or shear treatment comprising discrete particles derived from a granule according to the invention. Such foodstuff is provided having an improved texture and/or appearance, especially being

short, smooth or shiny. The invention also provides use of a starch granule and/or method according to the invention in the preparation of foodstuff subject to heat and or shear treatment to improve texture and/or taste of said foodstuff. The invention is further explained in the detailed description herein without limiting the invention.

Detailed description

Preparation of hydroxypropylated crosslinked starches

A 39% starch slurry was prepared from different raw materials. To this slurry was added sodium sulfate (100 g/kg starch) and sodium hydroxide (7.5 g/kg starch) as a 4.4 % solution. The temperature was raised to 35 °C and sodium trimetaphosphate (NaTMF) was added. For low crosslinked starches 625 mg NaTMF/kg starch was used, low being defined as varying between 325 to 1000 mg NaTMF/kg starch or functionally equivalent with other cross-linking agents, the high crosslinked starches were prepared with 2500 mg NaTMF/kg starch, high being defined as varying between 1000 to 3500 mg NaTMF/kg starch or functionally equivalent with other cross-linking agents. Next, propylene oxide (DS_{max} = 0.33) was introduced and the reaction was allowed to proceed for 20-24 hours. The slurry was neutralized with sulfuric acid to a pH of 5-6 and washed and dried by using conventional means known to the art. The raw materials used were amylopectin potato starch, normal potato starch and waxy maize starch and degraded potato starch. For the degradation of potato starch, different methods were used such as acid degradation, oxidative degradation or enzymatic degradation, employing conditions well known in the art. For example, a 39% starch slurry was treated with 10 N H₂SO₄ (in a quantity corresponding to 0.5-20 mol%, or with

sodium hypochlorite with a quantity corresponding to 0.1-5% Cl_2 for 6-24 hours at 35-55, preferably 45°C. After washing and drying the product was used as a raw material for the hydroxypropylation and cross-linking. Preferably higher cross-link levels then 625 mg NaTMF were used due to the lower molecular weight of the degraded starches.

Viscosity and disintegration measurements

10

A slurry containing 5% hydroxypropylated and crosslinked starch on a dry weight basis was prepared and heated in a Brabender viscograph following a temperature profile. First the suspension was heated to 45 °C rapidly, then the mixture was heated to 90 °C at a rate of 1.5 °C/min and kept at this temperature for 20 min. Finally the solution was cooled to 25 °C at a rate of 1.5 °C/min. From the solution thus obtained the viscosity was measured on a Brookfield apparatus and a microscopic picture was taken of the solution which was diluted in some cases. Next the solution was exposed to high shear conditions (Ultraturrax, 10000 rpm) for one and two minutes and the same measurements were performed. Apart from these measurements the texture of the solutions was investigated.

25

Table 1 shows the results of the viscosity measurements and Table 2 the results of the microscopic pictures of the solutions (see figures 1 to 16 for the photographs).

30

Table 1 - Viscosity measurements

starch	crosslink level	Brookfield (mPas)		
		for shear	after 1 min. shear	after 2 min. shear
amylopectin	low	37350	28200	23750 --
amylopectin	high	104	1980	1330 .
normal PS	low	1330	12066	10440
normal PS*	high	-	-	-
waxy maize	low	2000	3490	3110
waxy maize	high	18	-	64
acid degr. PS**	low	11760	-	980
acid degr. PS**	high***	14000	-	6050

*the high crosslinked normal potato starch was too thin for a good measurement.

5 **6% concentration

***high is 1250 mg NaTMF/kilo starch (20% moisture)

Table 2 - Microscopic pictures

starch	crosslink level	disintegration level of particles		
		before shear	after 1 min. shear	after 2 min. shear
amylopectin PS	low	big, swollen	mostly dis-integrated, small	completely disintegrated, very small
amylopectin PS	high	medium size, swollen	partly dis-integrated	mostly dis-integrated, small
normal PS	low	small, swollen	big, swollen	very big, swollen
normal PS	high	small, swollen	-	medium size, swollen
waxy maize	low	medium size, swollen	mostly dis-integrated, small	completely disintegrated, very small
waxy maize	high	small, swollen	-	small, swollen
acid degr, PS	low	large swollen	-	very small disintegrated
acid degr. PS	high	large swollen	-	small, disintegrated

- 5 Disintegration only takes place with the waxy and with the degraded derivatives. Both high and low crosslinked amylopectin potato starch show disintegration whereas only the lower crosslinked waxy maize derivative disintegrated under the applied shear. The amylopectin
- 10 and the degraded potato starch derivative with the lowest crosslink level after shear consisted of smaller particles than the derivatives with the higher crosslink level.

All potato starch derivatives before shear essentially have a pulpy, coarse or dull texture. After shear the amylopectin and the degraded derivatives have changed to a smooth, shiny and short paste. The lower crosslinked amylopectin potato derivative is more cohesive than the higher crosslinked derivative which is similar to the waxy maize derivative after shear. The degraded potato starch derivative gave a low viscous shiny dispersion while the higher crosslinked derivative gave a viscous paste comparable to the higher crosslinked amylopectin potato starch derivative. The normal potato starch products stay pulpy and dull after shear. The waxy maize derivatives become more shiny, smooth and creamy after shear but the difference between the paste before and after shear is not so explicit as for the amylopectin potato starch derivatives. Of all the derivatives only the lowest crosslinked amylopectin potato starch gave a clear paste which makes it very suitable for application in a fruitfilling. The results are summarised in the following two tables.

Table 3 - Texture of the 5% solutions before shear

starch	crosslink level	appearance
amylopectin	low	viscous, pulpy, dull
amylopectin	high	thin, coarse, dull
normal PS	low	medium viscous, pulpy, dull
normal PS	high	very thin, coarse, dull
waxy maize	low	medium viscous, reasonable shiny, blind
waxy maize	high	very thin, reasonable shiny, blind
acid degr. PS*	low	viscous, pulpy, dull
acid degr. PS*	high	viscous, pulpy, dull

*6% solutions

5 Table 4 - Texture of the 5% solutions after 2 min. shear

starch	crosslink level	appearance
amylopectin	low	highly viscous, short, shiny, smooth, cohesive, clear
amylopectin	high	viscous, shiny, smooth
normal PS	low	viscous, pulpy, dull
normal PS	high	thin, coarse
waxy maize	low	medium viscous, shiny, smooth, short, creamy, cohesive, blind
waxy maize	high	thin, shiny, blind
acid degr. PS*	low	thin, shiny, clear
acid degr. PS*	high	viscous, shiny, smooth, reasonably clear

*6% solutions

10 When hydroxypropylated crosslinked amylopectin or degraded potato starch is used in an application where high shear is involved in the procedure a smooth and

shiny product is obtained. Amylopectin potato starch products with a low crosslink level are very clear and have a cohesive structure. This cohesiveness is also found in similar waxy maize derivatives but the latter lack the clearness. Amylopectin potato starch products with a higher crosslink level are not clear and less cohesive but still smooth and shiny. Degraded potato starch derivatives with a high crosslink level behave similar while the lower crosslink level gives a low viscous dispersion consisting of small particles. Normal potato starch derivatives give under the high shear conditions pastes with pulpy and dull textures. On a granule level it was observed that the big swollen particles of amylopectin and degraded potato starch paste disintegrate under influence of high shear which is not observed with a similar normal potato starch derivative. This phenomenon accounts for the texture differences. Maize derivatives also disintegrate but this was only observed on a low crosslink level.

A hydroxypropylated and crosslinked derivative of amylopectin or degraded potato starch derivatives give smooth, short and shiny textures when they are cooked and a certain amount of shear is applied (jetcooking). A similar derivative of normal potato starch does not have these features. When this derivative is jetcooked the solution gave a dull and pulpy texture. In some applications such as dressings, fruitfillings and puddings the smooth and shiny texture is desired while in other applications such as tomato sauce the pulpy texture is preferred. The observed difference is caused by the ease of granular disintegration of the amylopectin and degraded derivative compared to the normal potato starch derivative. To visualize this effect some hydroxypropylated amylopectin potato starch, acid degraded potato starch, normal potato starch and waxy maize derivatives with two degrees of crosslinking were prepared and investigated after heating under low-shear conditions and after high-shear conditions. Microscopic

pictures were taken from the solutions to visualize the difference in particle size.

Food examples.

5

Spoonable dressings

Equipment Fryma colloidal mill

10 Dressing A (pH 4,3-4,4)

Ingredients

	%	g
Starch derivative	6,0	180
Paselli MD10	5,0	150
Powdered sugar	2,0	60
Salt	1,5	45
Sodium benzoate	0,1	3
Potassium sorbate	0,1	3
Vinegar (5%)	8,0	240
lemon juice	0,8	24
Mustard	1,0	30
Egg powder (whole)	2,4	72
Oil	2,0	60
Tap water	71,1	2133
Total	100,0	3000

15

Dressing B (pH 3,6-3,70)

	%	g
Starch derivative	6,0	180
Paselli MD10	5,0	150
Powdered sugar	5,0	150
Salt	1,5	45
Sodium benzoate	0,1	3
Potassium sorbate	0,1	3
Vinegar (5%)	10,0	300
Citric ad	0,4	12
Mustard	1,0	30
Egg powder (whole)	2,4	72
Oil	2,0	60
Tap water	66,5	1955
Total	100,0	3000

Preparation procedure

- 5
- Mix in a plastic bag the dry ingredients (except egg powder)
 - Mix in a bowl the vinegar, the lemon juice and 1833 of the
- 10 water
- Mix the dry ingredients in the liquid and heat while stirring
on a steam bath for 15 min.
 - Cool to 20 °C
- 15
- Mix the egg powder with the remaining and add the mustard
 - Create a vacuum in the Fryma of 500 mbar
 - Turn on the scrapers and fill the Fryma with the starch mixture
- 20
- Add the egg/mustard mixture
 - After 30 sec. add the oil (also in 30 sec.)
 - Mix in the Fryma for another 30 sec.
 - From this the dressing is obtained.

Tomato sauce**Ingredients**

5

	%
Tomato puree	15,0
Starch derivative	4,0
Salt	2,5
Powdered sugar	12,5
Vinegar (5 %)	12,5
Sodium benzoate	0,1
Potassium sorbate	0,1
Tap water	53,3
Total	<u>100,0</u>

Preparation procedure

- Mix the dry ingredients
- 10 - Mix, water and the tomato puree in a sauce pan
- Add the dry ingredient mix to the liquid
- Heat while stirring to 90-95 °C
- Heat for 15 min at this temperature
- Cool to 20 °C

15

Tomato soup

Ingredients

5

	g	%
Tap water	345,0	86,25
Tomato puree	28,0	7,00
Starch derivative	16,0	4,00
Sugar	4,0	1,00
Salt	3,0	0,75
Sun flower oil	1,6	0,40
Tomato taste 2M-18322	1,2	0,30
Bouillon taste 34099	0,8	0,20
MSG	0,4	0,10
Total	400,0	100,00

Preparation procedure

- 10 - The ingredients, except the starch derivative, are mixed in beaker
- The mixture is heated to 45-50 °C while stirring
 - The solution is cooled to 25-30 °C
- 15 - 16,0 g of starch derivative is weighed into a can
- The can is filled with the solution to a total of 400 g
 - The can is closed and shaken
 - The is sterilized for 55 min at 120 °C

20

UHT pudding (Dutch style)**Ingredients**

			%
Skimmed milk powder	3150	g	9,3
Sugar	2310	g	6,8
Starch derivative	1380	g	4,1
Colour/taste	39	g	0,12
Salt	15	g	0,04
Satiagel HMR	7,5g		0,02
Tap water	27	L	79,6

5

preparation procedure

In a vessel 27 L water is given. To this the milk powder is added and suspended by stirring. The rest of the ingredients is mixed and after 5 min added to the milk. The suspension is pumped to a buffer tank and heated through a plate-exchanger to 80 °C and transferred to a jet cooker and cooked at 140 °C for a few seconds. The pudding is cooled to 40 °C and filled into cups that are subsequently sealed.

15

Gel strength measurement

20

The gel strength of the dressing is measured on a Stevens LFRA apparatus using a TA 11 plunger with a speed of 2 mm/s and a penetration depth of 40 mm.

25

A spoonable dressing was prepared according to procedure A. The gel strength of the products was determined. The results are summarised in table 5. Also the products were evaluated for their sensoric properties.

30

Table 5. Stevens gel strength (in mPas) of a spoonable dressing prepared according to procedure A

Product	starch	gel strength after 1 day	gel strength after 1 week	gel strength after 1 month	gel strength after 6 months
A	APS	81	82	98	150
B	WMS	71	76	92	159
C**	PS	25	25	-	-

** Product low viscous, phase separation after 1 week

The dressings of based on the products A and B were both shiny directly after preparation. After 6 months, however, they were slightly gelled and somewhat dull. This could be reversed with stirring by hand. The dressing based on product C was low viscous and had a pulpy, dull texture. After two weeks phase separation in the dressing of product C was observed.

In the before mentioned dressing the pH of the system is about 4,3. The pH can have large influence on the properties of products depending on the modification and the type of starch. In table 6 the results are summarised for a more acidic type of dressing.

Table 6 Stevens gel strength (in mPas) of dressings prepared according to procedure B

Product	starch	gel strength after 1 week	gel strength after 1 month	gel strength after 2 months	gel strength after 6 months
D	APS	150	170	180	250
E	WMS	140	170	190	250

The dressings were both shiny directly after preparation. After 6 months, however, they were slightly gelled and somewhat dull. This could be reversed with stirring by hand.

5

As a third possibility amylopectin potato starches can be applied in tomato sauce. The results have been summarised in table 7.

10 Table 7 Gel strength and viscosity of tomato sauce

Product	starch	Modifi- cation	Stevens	Brookfield HAT	Brookfield RVT
F	WMS	Adip-ac	60	11600	17000
G	APS	NaTMF-ac	75	14200	16000
H	APS	Adip-ac	72	13400	14800

The tomato sauces based on all product were shiny and short. Potato starch derivatives give pulpy textures which are sometimes preferred.

15

Table 8 Viscosity of tomato soups

Product	starch	Modifi- cation	Viscosity in mPas after....		
			1 month	3 months	6 months
F	WMS	Adip-ac	8080	5180	6300
E	WMS	POCl ₃ - HP	9340	7860	8280
I	APS	Adip-ac	8540	7140	5900
J	APS	NaTMF- HP	9440	9480	10400

The conclusion from the experiments is that the viscosity of the soups based on APS and WMS is comparable. The texture of all soups is short and shiny.

20

The conclusion from the food examples is that due to granular disintegration amylopectin potato starch

derivatives give short, shiny textures comparable to non disintegrated waxy cereal derivatives. (Waxy) cereal starches have the draw back that they have a less desirable taste and that they sometimes cannot be applied
 5 in some food systems due to religious restrictions.

Table 9

Processing equipment and conditions affecting starch performance

Equipment	Conditions
Steam jacketed kettle	Low shear, long cook and cooling times
Swept surface cooker and cooler	Medium shear, fast cooking and cooling times
Steam infusion cooker	Medium shear, high temperature, short cooking time
Pumping equipment	Medium to high shear
Steam injection (jet) cooker	Medium/high shear, fast cook, high temperature
Swept surface cooker with flash cooling	High shear, fast cook and cooling times
Plate heat exchange cooker and cooler	High shear, short cooking and cooling times
Colloid mill	Very high shear

10

Note: Steam jacketed kettles with sweeping mixers are normally considered as low in shear; steam injection and plate cookers as medium in shear; plate coolers, flash coolers and milling equipment as high, and homogenisers
 15 as extremely high in shear. This is a general statement, damage of course also depends on the length of treatment and on the temperatures used. It is for example possible that a steam jacketed kettle may do as much damage to the starch granule over an extended time as an homogeniser in
 20 a short time.

Figure legends

Figure 1

Amylopectine PS with low cross-link level before shear.

5

Figure 2

Amylopectine PS with low cross-link level after 1 min. shear.

10 Figure 3

Amylopectine PS with low cross-link level after 2 min. shear.

Figure 4

15 Amylopectine PS with high cross-link level before shear.

Figure 5

Amylopectine PS with high cross-link level after 1 min. shear.

20

Figure 6

Amylopectine PS with high cross-link level after 2 min. shear.

25 Figure 7

Normal PS with low cross-link level before shear.

Figure 8

Normal PS with low cross-link level after 1 min. shear.

30

Figure 9

Normal PS with low cross-link level after 2 min. shear.

Figure 10

35 Normal PS with high cross-link level before shear.

Figure 11

Normal PS with high cross-link level after 2 min. shear.

Figure 12

5 Waxy maize starch with low cross-link level before shear.

Figure 13

Waxy maize starch with low cross-link level after 1 min. shear.

10

Figure 14

Waxy maize starch with low cross-link level after 2 min. shear.

15 Figure 15

Waxy maize starch with high cross-link level before shear.

Figure 16

20 Waxy maize starch with high cross-link level after 2 min. shear.

Figure 17

25 Degraded potato starch with high crosslink level before shear.

Figure 18

Degraded potato starch with high crosslink level after 2 min. shear.

30

Figure 19

The number average particle size distribution of starch in a retorted dessert. Line A is the distribution of an amylopectin PS derivative, line B the distribution of a normal PS derivative. The use of the amylopectin PS derivative results in a dessert with a smooth and shiny texture which is greatly appreciated by customers. Use of normal PS results in a coarse, blind or dull dessert

35

[illegible]

CLAIMS

1. A method for providing a foodstuff with a short or smooth texture and/or shiny appearance after heat and/or shear treatment comprising adding to the ingredients of said foodstuff a cross-linked starch selected for its capacity to disintegrate into discrete particles after processing.
2. A method according to claim 1 wherein said cross-linked starch is non-cereal starch.
3. A method according to claim 1 or 2 wherein said starch is degraded.
4. A method according to anyone of claims 1 to 3 wherein said starch has an amylopectin:amylose ratio of at least 90:10, preferably at least 95:5, more preferably at least 99:1.
5. A composition comprising a cross-linked starch for use in a method according to anyone of claims 1 to 4.
6. A composition according to claim 5 wherein said starch is non-cereal starch.
7. A composition according to claim 5 or 6 wherein said starch has an amylopectine:amylose ratio of at least 90:10, preferably at least 95:5, more preferably at least 99:1.
8. A composition according to anyone of claims 5 to 7 wherein said starch is derived from a genetically modified potato plant mutant or from an amylose-free potato plant mutant.
9. A composition according to anyone of claims 5 to 8 wherein said starch has been subjected to stabilisation.
10. Use of a cross-linked starch in the preparation of a foodstuff wherein the starch granules disintegrate into discrete particles.
11. A foodstuff obtainable by using a method according to anyone of claims 1 to 4.

12. A foodstuff comprising discrete particles derived from a starch granule.

12. A foodstuff comprising discrete particles derived from a starch granule.




Figure 1 - Amylopectin PS with low crosslink level before shear




Figure 2 - Amylopectin PS with low crosslink level after 1 min. shear




Figure 3 - Amylopectin PS with low crosslink level after 2 min. shear




Figure 4 - Amylopectin PS with high crosslink level before shear




Figure 5 - Amylopectin PS with high crosslink level after 1 min. shear




Figure 6 - Amylopectin PS with high crosslink level after 2 min. shear




Figure 7 - Normal PS with low crosslink level before shear



Figure 8 - Normal PS with low crosslink level after 1 min. shear




Figure 9 - Normal PS with low crosslink level after 2 min. shear




Figure 10 - Normal PS with high crosslink level before shear




Figure 11 - Normal PS with high crosslink level after 2 min. shear




Figure 12 - Waxy maize starch with low crosslink level before shear




Figure 13 - Waxy maize starch with low crosslink level after 1 min. shear




Figure 14 - Waxy maize starch with low crosslink level after 2 min. shear



Figure 15 - Waxy maize starch with high crosslink level before shear





Figure 16 - Waxy maize starch with high crosslink level after 2 min. shear


09/936344



AVEBE/BU NB

Figure 17

Degraded potato starch with high crosslink level before shear.



AVEBE/BU NB

Figure 18

Degraded potato starch with high crosslink level after 2 min. shear.





Figure 19



Declaration and Power of Attorney Patent Application (Design or Utility)

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled: "Foodstuff containing discrete starch particles".

the specification of which

☐ is attached hereto
☒ was filed on September 10, 2001 as application serial no. 09/936,344
and or PCT International Application number PCT/NL00/00174 and was amended
on (if applicable).

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose to the U.S. Patent and Trademark Office all information know to me to be material to patentability as defined in 37 C.F.R. §1.56.

I hereby claim foreign priority benefits under 35 U.S.C. §119(a)-(d) or 35 U.S.C. §365(b) of any foreign application(s) for patent or inventor's certificate, or 35 U.S.C. §365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below any foreign application for patent or inventor's certificate of PCT International application having a filing date before that of the application on which priority is claimed.

Prior Foreign Application(s)		
Number 99200829.2	Country EP	Day/Month/Year Filed 17 March 1999
Number	Country	Day/Month/Year Filed
Number	Country	Day/Month/Year Filed

I hereby claim the benefit under 35 U.S.C. §119(e) of any United States provisional application(s) listed below:

Prior Provisional Application(s)	
Serial Number	Day/Month/Year Filing Date
Serial Number	Day/Month/Year Filing Date
Serial Number	Day/Month/Year Filing Date

I hereby claim the benefit under 35 U.S.C. §120 of any United States application(s), or under 35 U.S.C. §365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of 35 U.S.C. §112, I acknowledge the duty to disclose to the U.S. Patent and Trademark Office all information known to me to be material to patentability as defined in 37 C.F.R. §1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application:

Prior U.S. or International Application(s)		
Serial Number	Day/Month/Year Filed	Status (patented, pending, abandoned)
Serial Number	Day/Month/Year Filed	Status (patented, pending, abandoned)
Serial Number	Day/Month/Year Filed	Status (patented, pending, abandoned)

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements are made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under 18 U.S.C. §1001 and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Power of Attorney

As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith.

Attorney

Registration Number


Charles R. Hoffmann	<u>24,102</u>
Ronald J. Baron	<u>29,281</u>
Gerald T. Bodner	<u>30,449</u>
A. Thomas Kammer	<u>28,226</u>
Irving N. Feit	<u>28,601</u>
Alan M. Sack	<u>31,874</u>
Algis Anilionis	<u>36,995</u>
Gregory W. Bachmann	<u>41,593</u>
Anthony E. Bennett	<u>40,910</u>
James F. Harrington	<u>P-44,741</u>
Glenn T. Henneberger	<u>36,074</u>
Richard LaCava	<u>41,135</u>
Kevin E. McDermott	<u>35,946</u>
Robert C. Morriss	<u>42,910</u>
Samir R. Patel	<u>P-44,998</u>
R. Glenn Schroeder	<u>34,720</u>
Susan A. Sipos	<u>43,128</u>
Roderick S.W. Turner	<u>38,639</u>
Steven T. Zuschlag	<u>43,309</u>

(19)

I hereby authorize them or others whom they may appoint to act and rely on instructions from and communicate directly with the person/organization who/which first sends this case to them and by whom/which I hereby declare that I have consented after full disclosure to be represented unless/until I instructed otherwise.

Please direct all correspondence in this case to at the address indicated below:

Ronald J. Baron
Hoffman & Baron, L.L.P.
6900 Jericho Turnpike
Syosset, New York 11791
United States of America

Full Name of Sole or First Inventor		
Family Name Buwalda	First Given Name Pieter	Second Given Name Lykle
Residence and Citizenship		
City of Residence Groningen	State or Country of Residence the Netherlands	Country of Citizenship the Netherlands
Post Office Address		
Street Address Mondriaanstraat 32	City Groningen	State & Zip Code or Country 9718 MJ
Signature of Inventor 		Date 24-9-01

Full Name of Second Inventor, if any		
Family Name Bleeker	First Given Name Ido	Second Given Name Pieter
Residence and Citizenship		
City of Residence Ten Boer	State or Country of Residence the Netherlands	Country of Citizenship the Netherlands
Post Office Address		
Street Address Poldermolen 22	City Ten Boer	State & Zip Code or Country 9791 LS
Signature of Inventor		Date Sept, 24, 2001

Full Name of Third Inventor, if any		
Family Name Wolltjes	First Given Name Jakob	Second Given Name Roelf
Residence and Citizenship		
City of Residence Veendam	State or Country of Residence the Netherlands	Country of Citizenship the Netherlands
Post Office Address		
Street Address Groningenlaan 42	City Veendam	State & Zip Code or Country 9642 EJ
Signature of Inventor		Date 24-9-01

Full Name of Fourth Inventor, if any		
Family Name Semeijn	First Given Name Cindy	Second Given Name
Residence and Citizenship		
City of Residence Groningen	State or Country of Residence the Netherlands	Country of Citizenship the Netherlands
Post Office Address		
Street Address Fongersplaats 96	City Groningen	State & Zip Code or Country 9725 LD
Signature of Inventor		Date 24-9-01

VEREENIGDE is the trade name of Vereenigde Octrooibureaux, a partnership of private limited companies. Vereenigde Octrooibureaux only accepts liability insofar as its mandatory professional third party liability insurance provides for compensation.

the history thereof; and generally do everything possible which said Assignee, its successors, assigns or representatives shall consider desirable for aiding in securing and maintaining proper patent protection for said improvements and for vesting title to said improvements and all applications for patent and all patents on said improvements, in said Assignee, its successors, assigns and legal representatives; and

Covenant with said Assignee, its successors, assigns and legal representatives that no assignment, grant, mortgage, license or other agreement affecting the rights and property herein conveyed has been made to others by the undersigned, and that full right to convey the same as herein expressed is possessed by the undersigned.

Date 21-9-01

Date Sept, 21, 2001

Date 21-9-01

Date 21-9-01


[Signature] P.L. Buwalda

[Signature] F.P. Bleeker

[Signature] J.R. Wolltjes

[Signature] C. Semeijn

United States Patent & Trademark Office
Office of Initial Patent Examination -- Scanning Division



Application deficiencies found during scanning:

☐ Page(s) _____ of _____ were not present
for scanning. (Document title)

☐ Page(s) _____ of _____ were not present
for scanning. (Document title)

☒ *Scanned copy is best available. Drawings are dark.*